

## Materialsammenligning

Materialtype	Tyskland	Werkstoffnr.	Sverige (SS)	USA (ASTM)
<b>Støpejern</b>	GG20	0.6020	0120	A48NO30B
	GG22	0.6022	-	-
	GG25	0.6025	0125	A48NO30B
<b>Seigjern</b>	GGG40	0.7040	0417-00	-
	GGG40.3	0.7043	0717-12	-
	GGG50	0.7050	0727	-
<b>Stål</b>	RSt37-2	1.0114	1312	-
	St35.8/1	1.0305	1330	-
	C22.8	1.0460	-	-
	C35	1.0501	1550	-
	GS-C25	1.0619	2172	-
	St52-3N	1.0841	-	-
<b>Rustfrie stål</b>	G-X7Cr13	1.4001	2301	-
	X12CrMoS13	1.4005	2380-03	AISI1416
	G-X12CrS13	1.4008	2302	A296 CA-15
	X20Cr13	1.4021	2303-3	AISI420
	X12CrMoS17	1.4104	2383-02	AISI430F
	X35CrMo17	1.4122	-	-
	X5CrNi1810	1.4301	2332-02/2333-02	AISI304
	X10CrNiS189	1.4305	2346-02	AISI303
	X2CrNi1911	1.4306	2352	AISI304L
	G-X6CrNi189	1.4308	2333	-
<b>Syrefaste stål</b>	X5CrNiMo17122	1.4401	2347-02	AISI316
	G-X6CrNiMo1810	1.4408	2343	-
	X5CrNiMo17133	1.4436	2343-02	AISI316
	X8CrNiMo2752	1.4460	2343-02	AISI329
	X6CrNiTi1810	1.4541	2337-02	AISI321
	X6CrNiMoTi17122	1.4571	2350-02	AISI316Ti
	-	-	2343	A351CF8M